

Code N° M5202--

Series of inks for transfer sublimation printing, compatible with PANASONIC piezo printheads.

**DIGITAL SUBLIMATION INK FOR TRANSFER PRINTING**

- Ideal for transferring onto synthetic fabrics (polyester)

**APPLICATION VERSATILITY**

- Ideal for sportswear, promotional items, curtaining, flags, banners, interior decoration

**COMPATIBLE WITH PANASONIC PRINTHEADS**

- Compatible with the above-mentioned piezo printheads

**GENERAL FEATURES**

- Very vivid and bright colours, allowing to achieve a wide colour space during profiling
- High colour concentration
- Good general fastness
- Excellent drying quickness of the printed paper
- Excellent release (transfer) capacity

**PRODUCTS OF THE SERIES**



COLOUR	BLACK PLUS	CYAN	MAGENTA	YELLOW
CODE	520211	520251	520230	520215
PACKING	2 litres	2 litres	2 litres	2 litres
SHELF LIFE	15 months	15 months	15 months	15 months



COLOUR	LIGHT CYAN	LIGHT MAGENTA	YELLOW FLUO	PINK FLUO
CODE	520252	520231	520216	520234
PACKING	2 litres	2 litres	2 litres	2 litres
SHELF LIFE	15 months	15 months	15 months	15 months

**DIRECTIONS**

It is recommended to let the product reach operative conditions in terms of temperature and humidity at least 24 hours prior to use, taking care of not stirring it, and apply the product under controlled conditions:

- **RECOMMENDED TEMPERATURE RANGE:** 20-25°C
- **RECOMMENDED HUMIDITY RANGE:** 40-60%

The ink is ready to use.

The printed paper must be transferred hot, through calender or flat press, at a temperature between **180-220°C** during a varying time, between **180" and 30"**.

Time and temperature may vary, depending on the type and nature of the material, which the transfer is made onto.

**AUXILIARIES – FLUIDS FOR PLOTTER MAINTENANCE**

- **DIGISTAR CAPPING FLUID (CODE 408703):** this product has moistening and anti-scaling properties, available in 250 ml container with dosing pipette for application on "capping station".
- **DIGISTAR CLEANER (CODE 408501):** this product is used for cleaning the ink feeding circuits.
- **DIGISTAR CLEANER NFS (CODE 408503):** detergent product for cleaning of the ink feeding circuits, ideal for industrial equipment. DIGISTAR CLEANER NFS has been specially developed to limit the foam forming.

For further information, see the related technical data sheet.



**FASTNESS**

COLOUR	CODE	FASTNESS – EN ISO			SUBLIMATION CLASS
		105B02	105C10	105E04	
CYAN	520251	5-6	4-5	4-5	C
MAGENTA	520230	6-7	4-5	5	C
YELLOW	520215	6-7	4-5	4-5	B
BLACK PLUS	520211	5-6	4-5	4-5	B/C
LIGHT CYAN	520252	5-6	4-5	4-5	C
LIGHT MAGENTA	520231	6-7	4-5	5	C
YELLOW FLUO	520216	4	4-5	5	B
PINK FLUO	520234	4	4-5	5	C

FASTNESS - EN ISO	105B02	LIGHT FASTNESS
	105C10	WASHING FASTNESS
	105E04	PERSPIRATION FASTNESS

SUBLIMATION CLASS	A	T <sub>SUBLIMATION</sub> 180°C
	B	T <sub>SUBLIMATION E</sub> 190°C
	C	T <sub>SUBLIMATION</sub> 200°C
	D	T <sub>SUBLIMATION</sub> 210°C

FASTNESS RANGE: LIGHT FASTNESS: min 1, MAX 8 – WASHING FASTNESS: min 1, MAX 5 – PERSPIRATION FASTNESS: min 1, MAX 5

**STORAGE**

It is recommended to keep the product away from light and heat sources at a **temperature lower than 25° C.**

**SPECIAL INSTRUCTIONS**

- It is recommended to always make printing, drying and transfer tests onto the substrates which are meant to be used, so as to exactly determine features, working time and effects to be obtained.
- Extreme drying conditions near the printer carriage could compromise the quality of the prints.
- Require safety data sheets, available for all products, and always follow the contained instructions regarding all the specific information and the environmental safety.
- The ink performance is strictly connected to the used plotter model and printing procedure.

**IMPORTANT NOTE**

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk. While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.